



PRODUCT INFORMATION

Revised on January 2013

BH5200 BLACKHAWK GEL KOTE

DESCRIPTION:

A nonfibred asphalt based gel automotive undercoating that can be applied by airless spray equipment. Gel Kote offers excellent rust and corrosion protection on vehicle underbodies or on ferrous and nonferrous surfaces subjected to corrosive environments. Because of the gelling properties of this coating, coverage in difficult to access areas can be achieved without excessive build up.

Gel Kote is available in 55-gallon open head drums, 16-gallon kegs and quart bottles.

TYPICAL PROPERTIES:

| | |
|--|-----------|
| Application Temperature (Material), Deg. F..... | 50-120 |
| Flash Point Pensky Martens Closed Cup, Deg. F., Min..... | 100 |
| Solids Content, Weight %, Min..... | min 45 |
| Corrosion To Steel, Copper, Aluminum..... | None |
| Density, Lbs./Gal @ 77F..... | <8 |
| Dry To Touch, 1/32" Film, Hrs., Max..... | 2 |
| Resistance To Oils, Greases, Solvents..... | Poor |
| Storage Stability..... | Excellent |

APPLICATION:

15:1 and 30:1 displacement pumps are typical in spray applying this material. Please contact spray equipment manufacturer for further detail.

Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and material safety data sheets before using. While all statements, technical information, and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user.

Please contact ErgonArmor for further information at 877.982.7667 or FAX 601-933-3381. For all Terms and Conditions of Sale see ergonarmor.com.

ORDERING INFORMATION

For additional information, prices, or to place an order, please contact your ErgonArmor sales representative. If you do not know the name of your sales representative, call 877-98ARMOR.



A Division of Ergon Asphalt & Emulsions, Inc. | P.O. Box 1639, Jackson, MS 39215-1639
| 601-933-3381 Fax | 877-98ARMOR | ergonarmor.com